

SFF-15 Front-Lit



Starflex, Expert's choice

manufactured by **Starflex**



Features & Applications

- Width : 80cm (31")~ 220cm(87"), 250cm(98"), 320cm(125"), 380cm(150"), 420cm(165") and 530cm(210") seamless
- White opaque substrate for small and wide format front-lit display
- Soft and delicate surface
- Billboard, banners, building murals and in-store display
- Matt & glossy available • Weather resistant
- Printable with Vutek, Scitex, Nur, Mimaki, Roland, Mutoh, Jeti, Seiko and etc.

Specification

(1000Dx1000D, 12x12)

Properties	Test Method	Unit	Result
Transmittance	ASTM E 424 6.5.2	%	8.5
Tensile Strength	ISO 13934-1:1999 C.R.E.CUT STRIP METHOD	KGF/5CM	L : 202.6 W : 180.0
Tearing Strength	ISO 13937-2:2000 C.R.E.SINGLE TEAR METHOD	KGF	L : 20.6 W : 16
Elongation	ISO 13934-2:2000 C.R.E.CUT STRIP METHOD	%	L : 23.4 W : 28.4
Adhesion Strength	ISO 2411.C.R.E	KGF/5CM	7.8
Flexing Endurance at Low Temp.	DIN53351	CYCLES	16000
Resistance to Low Temp.	DIN53351		-20℃
Resistance to High Temp.	DIN53351		80℃
Resistance to Weathering	ASTM G26, XENON ARCLAMP, 18MIN SPRAY/2HRS., 100HRS. EXPOSURE		NO CHANGE
Practice for operating light-exp. With and without water	ASTM G26, METHOD A, TYPE B, WEATHER-O-METER	GRADE	4