

SFF-13 Front-Lit



Starflex, Image maker for your digital solution

manufactured by **Starflex**

Features & Applications

- Width : 80cm (31")~ 220cm(87"), 250cm(98"), 320cm(125"), 380cm(150"), 420cm(165") and **530cm(210") seamless**
- White opaque substrate for small and wide format front-lit display
- Soft and delicate surface
- Billboard, banners, building murals and in-store display
- Matt & glossy available • Weather resistant
- Printable with Vutek, Scitex, Nur, Mimaki, Roland, Mutoh, Jeti, Seiko and etc.

Specification

(1000Dx1000D, 9x9)

Properties	Test Method	Unit	Result
Transmittance	ASTM E 424 6.5.2	%	9.5
Tensile Strength	ISO 13934-1:1999 C.R.E.CUT STRIP METHOD	KGF/5CM	L : 139.0 W : 116.2
Tearing Strength	ISO 13937-2:2000 C.R.E.SINGLE TEAR METHOD	KGF	L : 11.4 W : 15.5
Elongation	ISO 13934-2:2000 C.R.E.CUT STRIP METHOD	%	L : 22.2 W : 29.3
Adhesion Strength	ISO 2411.C.R.E	KGF/5CM	13.7
Flexing Endurance at Low Temp.	DIN53351	CYCLES	16000
Resistance to Low Temp.	DIN53351		-20℃
Resistance to High Temp.	DIN53351		80℃
Resistance to Weathering	ASTM G26, XENON ARCLAMP, 18MIN SPRAY/2HRS., 100HRS. EXPOSURE		NO CHANGE
Practice for operating light-exp. With and without water	ASTM G26, METHOD A, TYPE B, WEATHER-O-METER	GRADE	4