

SBO-11, 15

Blockout



Starflex, Image maker for your digital solution

manufactured by **Starflex**

SBO-11, 15 Blockout

www.star-flex.com

Features & Applications

- Width : 80cm (31")~ 200cm(78"), 250cm(98") and 320cm(125")
- White opaque substrate for both sides display
- Newly designed & improved for delicate printability
- Softer surface
- Banners, exhibition decoration and in-store display
- Weather resistant
- Printable with Vutek, Scitex, Nur, Mimaki, Roland, Mutoh, Jeti, Seiko and etc.

31

Properties	Test Method	Unit	SBO-11	SBO-15
			Result	Result
Transmittance	ASTM E 424 6.5.2	%	0.3	<0.1
Tensile Strength	ISO 13934-1:1999 C.R.E.CUT STRIP METHOD	KGF/5CM	WARP : 59.8 WEFT : 48	WARP : 78.5 WEFT : 92.4
Tearing Strength	ISO 13937-2:2000 C.R.E.SINGLE TEAR METHOD	KGF	WARP : 1.8 WEFT : 0.9	WARP : 2.4 WEFT : 4.0
Elongation	ISO 13934-2:2000 C.R.E.CUT STRIP METHOD	%	WARP : 49.1 WEFT : 24.1	WARP : 39.9 WARP : 26.1
Adhesion Strength	ISO 2411.C.R.E	KGF/5CM	6	16.5
Flexing Endurance at Low Temp.	DIN 53351	CYCLES	13	30
Resistance to Low Temp.	DIN 53351 -20°C, 5HRS		WARP : 99.3 WEFT : 99.1	WARP : 99.4 WARP : 98
Resistance to High Temp.	DIN 53351 80°C, 5HRS		WARP : 98.1 WEFT : 97.9	WARP : 98 WEFT : 97.5
Practice for operating light-exp. With and without water	ASTM G 26, METHOD A, TYPE B, WEATHER-O-METER	GRADE	4	4